



## Data Sheet

### Product Description

EMS Material Designation	B200R
ASTM Type	TM13
Number of layers	3
Standard Marking	TRUFLEX B200R
Remarks	Intermediate Resistivity, General Purpose 0 to 300°F (-20 to 150°C)



### Chemical Composition

	<u>Grade</u>	<u>Chemistry</u>
High Expansion Alloy	Alloy B	22% Ni, 3% Cr, Bal Fe
Center Layer	Nickel	Ni
Low Expansion Alloy	Alloy 10	36% Ni, Bal Fe

### Thermostatic Properties

		ENGLISH		METRIC	
ASTM Flexivity	(50-200°F)	141	X 10 <sup>-7</sup> (in/in)/°F	--	
	(100-300°F)	140	X 10 <sup>-7</sup> (in/in)/°F	--	
Specific Curvature	(10-93°C)	--		25.4	X 10 <sup>-6</sup> (mm/mm)/°C
	(38-149°C)	--		25.2	X 10 <sup>-6</sup> (mm/mm)/°C
Maximum Sensitivity Temperature Range	0 to 300	°F		-20 to 150	°C
Useful Deflection Temperature Range	-100 to 700	°F		-70 to 370	°C
Recommended Maximum Temperature	1000	°F		540	°C
Electrical Resistivity @ 75°F (24°C)	189 to 211	*OCMF		0.314 to 0.351	μ-ohm-m

### Physical Properties

		ENGLISH		METRIC	
Density	0.300	Lb/in <sup>3</sup>		8.30	g/cm <sup>3</sup>
Modulus of Elasticity (E)	26	Msi		179	GPa

\*Ohms-Circular-Mil / Foot

Rev 0 - 11/21/2014