



## Data Sheet

### Product Description

EMS Material Designation	F125R
ASTM Type	--
Number of layers	3
Standard Marking	TRUFLEX F125R
Remarks	Intermediate Electrical Resistivity and Medium Flexivity



### Chemical Composition

	Grade	Chemistry
High Expansion Alloy	Alloy B	22% Ni, 3% Cr, Bal Fe
Center Layer	Copper	Cu
Low Expansion Alloy	Alloy 10	36% Ni, Bal Fe

### Thermostatic Properties

	ENGLISH		METRIC	
ASTM Flexivity (50-200°F)	148	$\times 10^{-7}$ (in/in)/°F	--	
Specific Curvature (10-93°C)	--		26.6	$\times 10^{-6}$ (mm/mm)/°C
Maximum Sensitivity Temperature Range	0 to 300	°F	-20 to 150	°C
Useful Deflection Temperature Range	-100 to 500	°F	-70 to 260	°C
Recommended Maximum Temperature	700	°F	370	°C
Electrical Resistivity @ 75°F (24°C)	119 to 131	OCMF*	0.198 to 0.218	$\mu$ ohms-m

### Physical Properties

	ENGLISH		METRIC	
Density	0.297	Lb/in <sup>3</sup>	8.22	g/cm <sup>3</sup>
Modulus of Elasticity (E)	25.0	Msi	172	GPa

\*Ohms-Circular-Mil / Foot

Rev 0 - 11/21/2014