



Data Sheet

Product Description

EMS Material Designation	F30R
ASTM Type	TM25
Number of layers	3
Standard Marking	TRUFLEX F30R
Remarks	Low Electrical Resistivity and Medium Flexivity



Chemical Composition

	Grade	Chemistry
High Expansion Alloy	Alloy B	22% Ni, 3% Cr, Bal Fe
Center Layer	Copper	Cu
Low Expansion Alloy	Alloy 10	36% Ni, Bal Fe

Thermostatic Properties

	ENGLISH		METRIC	
ASTM Flexivity (50-200°F)	140	$\times 10^{-7}$ (in/in)/°F	--	
Specific Curvature (10-93°C)	--		25.2	$\times 10^{-6}$ (mm/mm)/°C
Maximum Sensitivity Temperature Range	0 to 300	°F	-20 to 150	°C
Useful Deflection Temperature Range	-100 to 500	°F	-70 to 260	°C
Recommended Maximum Temperature	700	°F	370	°C
Electrical Resistivity @ 75°F (24°C)	28 to 32	OCMF*	0.047 to 0.053	μ ohms-m

Physical Properties

	ENGLISH		METRIC	
Density	0.305	Lb/in ³	8.43	g/cm ³
Modulus of Elasticity (E)	23.0	Msi	161	GPa

*Ohms-Circular-Mil / Foot

Rev 0 - 11/21/2014