



Data Sheet

Product Description

EMS Material Designation	P150R
ASTM Type	TM32
Number of layers	5
Standard Marking	TRUFLEX P150R
Remarks	Intermediate Resistivity, High Flexivity, General Use 0 to 400 °F (-20 to 200 °C)



Chemical Composition

	Grade	Chemistry
High Expansion Alloy	Alloy P	72%Mn-18%Cu-10%Ni
Center Layer	B-Plate	Alloy B / Cu / Alloy B
Low Expansion Alloy	Alloy 10	36% Ni, Bal Fe

Thermostatic Properties

	ENGLISH		METRIC	
ASTM Flexivity (50-200°F)	216	$\times 10^{-7}$ (in/in)/°F	--	
Specific Curvature (10-93°C)	--		38.9	$\times 10^{-6}$ (mm/mm)/°C
Maximum Sensitivity Temperature Range	0 to 400	°F	-20 to 200	°C
Useful Deflection Temperature Range	-100 to 500	°F	-70 to 260	°C
Recommended Maximum Temperature	800	°F	430	°C
Electrical Resistivity @ 75°F (24°C)	141 to 159	OCMF*	0.234 to 0.264	μ ohms-m

Physical Properties

	ENGLISH		METRIC	
Density	0.279	Lb/in ³	7.73	g/cm ³
Modulus of Elasticity (E)	19.0	Msi	131	GPa

*Ohms-Circular-Mil / Foot

Rev 0 - 11/21/2014