



## Data Sheet

### Product Description

<b>EMS Material Designation</b>	<b>SB300R</b>
<b>ASTM Type</b>	--
<b>Number of layers</b>	3
<b>Standard Marking</b>	<b>TRUFLEX SB300R</b>
<b>Remarks</b>	<b>Intermediate electrical resistivity with medium flexivity</b>



### Chemical Composition

	<u>Grade</u>	<u>Chemistry</u>
<b>High Expansion Alloy</b>	Alloy B	22% Ni, 3% Cr, Bal Fe
<b>Center Layer</b>	Steel	Fe
<b>Low Expansion Alloy</b>	Alloy 10	36% Ni, Bal Fe

### Thermostatic Properties

	ENGLISH		METRIC	
ASTM Flexivity (50-200°F)	146	$\times 10^{-7}$ (in/in)/°F	--	
Specific Curvature (10-93°C)	--		26.3	$\times 10^{-6}$ (mm/mm)/°C
Maximum Sensitivity Temperature Range	0 to 300	°F	-20 to 150	°C
Useful Deflection Temperature Range	-100 to 700	°F	-70 to 370	°C
Recommended Maximum Temperature	1000	°F	540	°C
Electrical Resistivity @ 75°F (24°C)	285 to 315	OCMF*	0.474 to 0.523	$\mu$ ohms-m

### Physical Properties

	ENGLISH		METRIC	
Density	0.294	Lb/in <sup>3</sup>	8.12	g/cm <sup>3</sup>
Modulus of Elasticity (E)	25.0	Msi	172	GPa

\*Ohms-Circular-Mil / Foot