



Product Description

EMS Material Designation	B300R
ASTM Type	TM15
Numer of Layers	3
Standard Marking	TRUFLEX B300R
Remarks	Intermediate Resistivity, General Purpose 0 to 300°F (-20 to 150°C)

Chemical Composition

	<u>Grade</u>	<u>Chemistry</u>
High Expansion Alloy	Alloy B	22% Ni, 3% Cr, Bal Fe
Center Layer	Nickel	Ni
Low Expansion Alloy	Alloy 10	36% Ni, Bal Fe

Thermostatic Properties

	ENGLISH	METRIC
ASTM Flexivity (50-200°F)	149 X 10 ⁻⁷ (in/in)/°F	
(100-300°F)	144 X 10 ⁻⁷ (in/in)/°F	
Specific Curvature (10-93°C)		26.8 X 10 ⁻⁶ (mm/mm)/°C
(38-149°C)		25.9 X 10 ⁻⁶ (mm/mm)/°C
Maximum Sensitivity Temperature Range	0 to 300°F	-20 to 150°C
Useful Deflection Temperature Range	-100 to 700°F	-70 to 370°C
Recommended Maximum Temperature	1000°F	540°C
Electrical Resistivity @ 75°F (24°C)	284 to 317 OCMF*	0.472 to 0.527 u-ohm-m

Physical Properties

	ENGLISH	METRIC
Density	0.297 Lb/in ³	8.22 g/cm ³
Modulus of Elasticity (E)	25.5 Msi	176 GPa

*Ohms-Circular-Mil / Foot